

G

<p>92-054171/07 L02            SHIKOKU SOGO KENKYU (TAKU)            17.04.90-JP-102233 (07.01.92) C04b-14/02 C04b-18/08 C04b-20            C04b-22/06 C04b-24 C04b-28/04            Cement compsn. for water-tight concrete - has amorphous silica            fines contg. discharged fly ash of specified size which is then            kneaded with aggregate and water            C92-024645</p>	<p>SHIK-17.04.90            *JO 4002-642-A            1/2-013, 2-014Q)</p>
<p>Full Patentees: Shikoku Sogo Kenkyu; Taisei Construction KK            Compsn is made by adding a suitable amt. of water reducing agent,            fly ash and amorphous silica fines in which the fly ash discharged on            firing coal is up to 20 microns in size. Resulting fly ash is then            kneaded with aggregate and water.            USE - Used for water-tight concrete for use at the underground            parts. (6pp Dwg.No.0/4)</p>	

BEST AVAILABLE COPY